

**Armstrong - Assay Composites**

Hole #                      From (m)    To (m)    Length (m)    % U3O8    % V2O5    g/t Ag            % Cu

<b>ML-AR-01</b>							
	15.1	15.6	0.5	0.04			

<b>ML-AR-02</b>							
	28.5	29.0	0.5	0.02			

<b>ML-AR-03</b>	No Significant Assays						
-----------------	-----------------------	--	--	--	--	--	--

<b>ML-AR-04</b>							
	195.6	197.1	1.5	0.04			
	216.6	217.6	1.0	0.03			
	270.0	277.2	7.2	0.06			
including	270.9	277.2	6.3	0.07			
including	270.9	273.3	2.4	0.10			

<b>ML-AR-05</b>	No Significant Assays						
-----------------	-----------------------	--	--	--	--	--	--

<b>ML-AR-06</b>							
	49.7	50.2	0.5	0.10			
	57.4	58.0	0.6	0.10			

<b>ML-AR-07</b>							
	18.7	19.2	0.5	0.05			
	49.5	50.1	0.6	0.06			
	55.2	55.7	0.5	0.06			

<b>ML-AR-08</b>							
	84.5	85.0	0.5	0.03			
	89.0	90.5	1.5	0.04			
	93.5	94.0	0.5	0.04			
	124.0	128.5	4.5	0.03			
including	127.0	128.5	1.5	0.06			

<b>ML-AR-09</b>							
	102.8	103.3	0.5	0.04			
	111.0	113.0	2.0	0.05			
including	112.0	112.5	0.5	0.11			
	156.0	161.4	5.4	0.07			
including	158.5	161.0	2.5	<b>0.09</b>			
including	159.0	160.0	1.0	<b>0.10</b>			

<b>ML-AR-10</b>							
	92.3	95.8	3.5	0.03			

**Armstrong - Assay Composites**

Hole #                      From (m)    To (m)    Length (m)    % U3O8    % V2O5    g/t Ag    % Cu

<b>ML-AR-11</b>		126.0	127.0	1.0	0.03		
-----------------	--	-------	-------	-----	------	--	--

<b>ML-AR-12</b>		163.2	172.3	9.1	0.03		
	including	167.5	170.4	2.9	0.05		
		184.1	186.1	2.0	0.03		

<b>ML-AR-13</b>		119.7	120.2	0.5	0.06		
		126.5	127.5	1.0	0.04		

<b>ML-AR-14</b>		96.5	99.8	3.3	0.13		
	including	97.5	99.5	2.0	0.20		
		176.3	178.5	2.2	0.10		

<b>ML-AR-15</b>		127.9	128.4	0.5	0.05		
-----------------	--	-------	-------	-----	------	--	--

<b>ML-AR-16</b>		99.5	101.0	1.5	0.04		
		109.5	111.0	1.5	0.04		
	including	110.0	111.0	1.0	0.05		

<b>ML-AR-17</b>		85.5	91.6	6.1	0.03		
	including	86.0	87.5	1.5	0.06		

<b>ML-AR-18</b>		119.1	121.0	1.9	0.06		
-----------------	--	-------	-------	-----	------	--	--

<b>ML-AR-19</b>		142.2	144.0	1.8	0.07		
		142.7	143.3	0.6	0.20		

<b>ML-AR-20</b>		56.0	56.5	0.5	0.02		
-----------------	--	------	------	-----	------	--	--

<b>ML-AR-21</b>		107.5	109.0	1.5	0.09		
	including	108.0	108.5	0.5	0.27		

<b>ML-AR-22</b>		172.3	172.8	0.5	0.03		
-----------------	--	-------	-------	-----	------	--	--

**Armstrong - Assay Composites**

Hole #                      From (m)    To (m)    Length (m)    % U3O8    % V2O5    g/t Ag       % Cu

<b>ML-AR-23</b>							
	59.5	60.0	0.5	0.03			

<b>ML-AR-24</b>							
	84.8	85.3	0.5	0.02			

<b>ML-AR-25</b>							
	21.3	22.8	1.5	0.03			

<b>ML-AR-26</b>							
	89.1	90.7	1.6	0.03			
including	180.4	189.9	<b>9.5</b>	<b>0.20</b>			
including	182.4	186.1	3.7	<b>0.50</b>			
including	184.0	185.6	1.6	<b>1.10</b>			

<b>ML-AR-27</b>							
	94.42	95.85	1.43	<b>0.12</b>			
	193.60	197.20	3.60	<b>0.14</b>	<b>0.26</b>	<b>15.2</b>	<b>0.45</b>

<b>ML-AR-28</b>							
	207.50	208.22	0.72	0.02			

<b>ML-AR-29</b>							
	32.40	36.40	4.00	<b>0.10</b>			
	183.35	184.65	1.30	0.06			
	230.75	232.25	1.50	0.03			

<b>ML-AR-30</b>							
	32.00	32.50	0.50	0.03			
	37.10	40.20	3.10	<b>0.07</b>			
including	37.10	38.70	1.60	<b>0.10</b>			
	276.14	276.64	0.50	0.03			

<b>ML-AR-31</b>							
	9.67	10.17	0.50	0.03			
	13.47	15.23	1.76	0.03			

<b>ML-AR-32</b>	No Significant Assays						
-----------------	-----------------------	--	--	--	--	--	--